

RUST-OLEUM®
INDUSTRIAL



SUPERGRIP® ANTI-SLIP SPRAY

**Makes every surface non-skid
in seconds**

- Light duty anti-slip finish
- Adheres to metal, wood, concrete, tile floors and parquet
- Also ideal for tools
- Very quick drying (5-10 minutes)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SUPERGRIP® ANTI-SLIP SPRAY

DESCRIPTION

This topcoat makes every surface Non-skid in a second. SuperGrip™ Anti-Slip sprays are based on a fast drying acrylic modified short oil alkyd. The coloured products are based on lead- and chromate free pigments and contain a special anti-slip additive. Should be applied on metal, concrete, ceramic and wood surfaces or properly prepared painted substrates.

RECOMMENDED USE

RUST-OLEUM Anti-Slip 2400 should be applied on metal, concrete, ceramic and wood surfaces or properly prepared painted substrates. Steel should be primed with 2169 or 2182. RUST-OLEUM Anti-Slip 2400 are intended for small maintenance jobs or for touch-up. RUST-OLEUM Anti-Slip 2400 should be used interior/exterior in light industrial exposures where anti slip characteristics are required.

DRY TIMES BY 20° C/RH 50%

| | |
|----------------|--------------------------|
| Touch dry: | 20 minutes |
| Dry to handle: | 60 minutes |
| Dry to recoat: | after 1 hour with itself |
| Fully cured: | 7 days |

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

25 µm

THEORETICAL CONSUMPTION

2,5 m² per spray can at 25 µm dry

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application

APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

APPLICATION & THINNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold the can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

REMARKS

Not for use in wet areas such as bathrooms or on substrates which are regularly in contact with water.

SAFETY DATA

| | |
|---------------------------|--|
| VOC level: | 524 - 538 g/l |
| Remarks regarding safety: | Consult Safety Data Sheet and Safety Information printed on the can. |

SHELF LIFE

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

Date issued: 22/11/2023

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu