

## TECHNICAL DATA SHEET

TDS: TMG150

### TEAMAC FARM OXIDE PAINT

430/G150

#### DESCRIPTION:

Teamac Farm Oxide Paint is a general purpose, versatile product giving economical protection and decoration.

#### RECOMMENDED USE:

Teamac Farm Oxide Paint can be used for the maintenance of structural steel, cladding etc., when applied to properly prepared surfaces. May be used coat on coat. Dries to a durable gloss finish.

#### AVAILABILITY:

5 litre, 20 litre

#### FINISH:

Gloss

#### COLOUR:

Red, Grey, Green, Black

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.12 - 1.31 @ 20 °C

#### VOLUME SOLIDS:

46 to 56%

#### WET FILM THICKNESS W.F.T

75 microns

#### DRY FILM THICKNESS D.F.T

35 - 40 microns

#### EXPECTED SPREADING RATE:

13 sq.m / litre  
@ 35 to 40 microns DFT

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

4.5 Poise @ 25 °C

#### FLASH POINT:

Above 32 °C (closed cup)

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 5 mins @ 20 °C

Hard dry: 24 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

12 hours or overnight

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

max 450 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application N/A  
restrictions

Method: Brush or roller Airless Spray

Thinner Thinners 14 Thinners 14  
(Max vol): (10%) (10%)

Nozzle size: 0.011" - 0.013"

Nozzle 1800 to 2000 psi  
pressure:

Cleaning Thinners 14  
solvent:

Recoat 12 hours or  
interval: overnight

**For further advice contact Teamac Technical Services on +44(0)1482 320194**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**TEAMAC**

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: [info@teamac.co.uk](mailto:info@teamac.co.uk)

[www.teamac.co.uk](http://www.teamac.co.uk)

**SURFACE PREPARATION:**

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminants.

Bare steel should be free from dust, rust and scale. Blast cleaning to SA 2½ is recommended. If blast cleaning is impractical, mechanical cleaning should be employed as hand cleaning does not clean the steel to the required degree. Any oil or grease should be removed with Coo-Var Degreaser before de-rusting. Where blast cleaning is carried out after assembly, special attention must be paid to edges, corners, nuts, bolts, welds etc. Welds should, if necessary be ground and all weld spatter, slag etc. must be removed.

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

As dictated by normal good painting practice. Care must be taken during application that the temperature is above the dew point to avoid any contamination. In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

Can be applied directly to prepared iron or steel. For greater protection prime with Teamac Zinc Phosphate Metal Primer.

**SUBSEQUENT COAT:**

Teamac Farm Oxide Paint

**REMARKS:**

SDS 10579, Black - SDS 10599

**ISSUED:**

08 August 2011

**REVISION:**

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

**HEALTH AND SAFETY:**

See safety data sheet - Red, Grey and Green -

**For further advice contact Teamac Technical Services on +44(0)1482 320194**

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**TEAMAC**  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: [info@teamac.co.uk](mailto:info@teamac.co.uk)  
[www.teamac.co.uk](http://www.teamac.co.uk)