

## TECHNICAL DATA SHEET

---

# Fungi-Shield

## Anti Mould and Blackspot Paint

<b>Description</b>	A water based, anti mould, algae and blackspot coating for interior walls and ceilings.			
<b>Finish</b>	Matt (FS42), Silk (FS43).			
<b>Features</b>	<ul style="list-style-type: none"> <li>• A washable, decorative, fungicidal anti mould paint for areas susceptible to mould and bacterial growth. Mould will not grow for the life of the paint film.</li> <li>• Non-toxic and odour free when dry. Non-caustic and non-injurious to the skin.</li> <li>• For areas subject to more frequent washing, Silk finish (FS43) is recommended. (Note: not recommended for use in extremely humid conditions).</li> <li>• This product is approved under the Control of Pesticides Regulations 1986, for use as directed. HSE No.7280.</li> </ul>			
<b>Complies With</b>	Matt: 2004/42/EC (2012) sub-category A(a) - VOC level below 30 g/l. Silk: 2004/42/EC (2012) sub-category A(b) - VOC level below 100 g/l.			
<b>Product Code</b>	Matt: <b>FS42</b> ; Silk: <b>FS43</b> .			
<b>Volume Solids</b>	Please consult Glixtone.			
<b>VOC's</b>	Matt: below 30 g/l; Silk: below 20 g/l.			
<b>Colour Range</b>	White and Magnolia. Can also be tinted to most pastel shades.			
<b>Film Thickness &amp; Coverage</b>	<b>Typical:</b>	<u><b>Dry</b></u> 30 µm	<u><b>Wet</b></u> 65 µm	<u><b>Theo. Coverage</b></u> 11 - 13 m <sup>2</sup> /l
	Coverage is between 11 – 13 m <sup>2</sup> /l per coat, depending on the type of surface, porosity, roughness and application.			
<b>Drying &amp; Overcoating Times</b> at Typical DFT	Surface Dry: Hard Dry: Overcoat Min: Overcoat Max:	<u><b>20°C</b></u> 1 h 2 - 4 h 2 - 4 h Indefinite		
	Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide for well ventilated areas.			

**TECHNICAL DATA SHEET**

---

**Fungi-Shield****Anti Mould and Blackspot Paint**

<b>Surface Preparation</b>	<ul style="list-style-type: none"><li>• Completely remove all traces of loose, flaking, soft and friable paint back to a clean firm surface by scraping and/or washing.</li><li>• Thoroughly abrade any glossy surfaces to achieve a good key.</li><li>• Make good any surface imperfections to original profile with a suitable filler and allow to dry thoroughly.</li><li>• Ensure that any grease, dirt, mould or rust is removed.</li><li>• During preparation, avoid the inhalation of dust. Wear a suitable face mask, if dry sanding. (Special precautions should be taken during surface preparation of pre-1960's surfaces over wood and metal as they may contain harmful lead. For further advice, please contact Glixtone.)</li><li>• <b>Copper or other metal surfaces</b> must be treated prior to the commencement of any painting. Bare copper or other metals must be either taped, or primed with an appropriate primer and allowed to full dry.</li><li>• <b>If there is mould or other organic growth</b>, remove by scraping or brushing with a stiff fibre brush (NOT a wire brush). Sterilise the affected areas by applying a liberal application of Glixtone Sterilising Solution and allow to dry for 24 hours (consult Technical Data Sheet for Glixtone Sterilising Solution before use).</li><li>• A second application of Glixtone Sterilising Solution is recommended for heavily infected areas.</li></ul>
<b>Mixing</b>	Thoroughly stir the coating before use.
<b>Mix Ratio</b>	Not applicable – single pack product.
<b>Application Conditions</b>	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. Do not apply the product when the ambient temperature falls below 10°C. The paint temperature at the time of application should ideally be 15° - 20°C.
<b>Application Details</b>	<ul style="list-style-type: none"><li>• The first coat of Fungi-Shield applied to bare areas may be thinned by up to 10% with water, to act as a sealer, prior to applying full coats.</li><li>• Apply two full coats of Glixtone Fungi-Shield.</li><li>• Remove splashes immediately from adjacent trim to be painted in conventional gloss finish.</li><li>• Note: if Glixtone Fungi-Shield is over-painted with anything other than itself, the fungicidal properties will be lost.</li></ul>
<b>Thinner/Cleaner</b>	Clean water.
<b>SG</b>	FS42 Matt: 1.39 ± 0.1 kg/l FS43 Silk : 1.26 ± 0.1 kg/l.
<b>Flash Point</b>	Above 60°C.
<b>Shelf Life</b>	1 year from date of manufacture when correctly stored in unopened containers.

## TECHNICAL DATA SHEET

---

### Fungi-Shield

#### Anti Mould and Blackspot Paint

<b>Storage</b>	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
<b>Health &amp; Safety</b>	Refer to the product's Safety Data Sheet (SDS) and safety advice on the product label before use.
<b>Date of Issue</b>	Jan 2024.

**A TRIMITE GLOBAL COATINGS BRAND**



Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use.