

# WOOD REPAIR FILLER (NATURAL)

## EASY TO SHAPE & QUICK DRYING ON INTERIORS & EXTERIORS

- ◆ WORKING TIME: 30 MINUTES
- ◆ EASY TO SAND
- ◆ COMPATIBLE WITH ALL PAINTS & COATINGS
- ◆ CAN BE DRILLED & SCREWED
- ◆ LOW ODOUR



### PURPOSE

Quick drying powder filler. Great for shaping and form work on all types of wood, indoors and out.

It has no depth limit and offers excellent adhesion.

Can be stained or painted with any type of conventional paint, varnish or stain after 3 hours.

### SUBSTRATES

Wood Repair Filler can be applied to any type of wood, including common exotic species, chipboard and plywood.

For optimal results, apply Wood Hardener beforehand.

### OVERCOATING

Wood Repair Filler can be overcoated by any type of conventional paints, varnishes and stains.

### Physical and technical FEATURES

- Wood Repair Filler: is a filler in powder form, for interior or exterior use, made of mineral extracts and selected binders.
- Characterization (NFT 36-005): Family IV - class 4c.
- Codification (NFT 30-608):  $G_3E_6S_2V_0W_0A_0C_0$ .
- Mixing rate: add 300ml water per 1kg powder (30%).
- Application thickness: no depth limit.
- Capacity: 1kg fills 1L when mixed.
- Working time: 30 minutes.
- Setting time: second coat as soon as the filler is hard and dry to the touch.
- Overcoating: can be painted in 3 hours average time (after complete drying).
- Color: natural wood.
- Adhesion: filler/substrate (NF T 30 608): > 0.8 Mpa.

### USE AND STORAGE CONDITIONS

- Application tools: filling knife, trowel or blade.
- Tool cleaning: after use, product residue can be rubbed off tools when dry (water cleaning is not necessary).
- Preservation: product guaranteed 6 months. Stored away from humidity. If found to be faulty within the guarantee period, we will arrange a replacement on proof of purchase.

### PACKAGING

Box: 1kg and 2kg.

### RECOMMENDATIONS and care for use

The times mentioned are indicative and depend on the substrate, coat thickness, and the ambient conditions.

Do not apply at a temperature below 5°C or above 35°C nor at a relative humidity over 80%.

### SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices. Substrates must be hard, cohesive, clean, sound and dry.

### NORMATIVE DOCUMENTS to be referred to

- NFT 30-608: Coating fillers for interior works and/or exterior.

### HEALTH AND SAFETY

It is recommended to wear gloves and glasses while applying Wood Repair Filler.

Always wear a dust mask when sanding.

Dispose of unused product and packaging responsibly at your local waste collection centre.

Safety data sheet available at [www.toupret.co.uk](http://www.toupret.co.uk)

The data sheet information, especially the guidelines relevant to the application and final use of the product are provided in good faith and result from TOUPRET's experience and knowledge of the products. The product should be used as per the trade practices rules book and in reference to our recommendations. The information provided is relevant to applications processed at a temperature of 20°C, a relative humidity of 50% and on average absorbency substrates. The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.



\* Information on the emission level of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on a scale from A+ (very low emissions) to C (high emissions).