

## ALBANY SUPER GLOSS

A quick drying water based gloss with good flow and opacity, for interior and exterior use.

### AVAILABILITY

Colour Refer to current Albany literature.

Packaging 1 & 2.5 litres.

### PROPERTIES

Drying time In good conditions: touch dry 2 hours and recoatable in 4-6 hours. Ensure previous coat is fully dry before application. At low temperatures or high humidity, drying times may be extended.

Finish Gloss.

Composition Pigment: Titanium Dioxide and Extenders.  
Binder: Alkyd Emulsion.  
Solvent: Water

Spreading rate Up to 15m<sup>2</sup> per litre depending on surface texture and porosity.

Wet film thickness 67 micrometres at 15m<sup>2</sup> per litre.

Dry film thickness 26 micrometres at 15m<sup>2</sup> per litre.

Volume solids 39 % White. Other colours will vary.

Flash point Not applicable

VOC content EU limit value for this product (cat.A/d): 130 g/l (2010). This product contains max. 4g/l VOC.

Limitations Do not apply when air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

### PREPARATION

#### New surfaces

Timber and Timber Based Boards (Including MDF) Treat any knots with two coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with Ready Mixed Filler. Rub down with a suitable grade of abrasive paper. Remove all dust. All surfaces must be suitable dry, and free from anything that will interfere with the adhesion of the materials to be applied. Prime with one coat of Albany Super Primer Undercoat.

All Metals Surfaces must be clean and free from anything that will interfere with the materials to be applied. Lightly abrade to a bright (not polished) surface – excluding galvanised surfaces. Wash with hot water and liquid detergent solution to remove oil, grease or any other contaminants, frequently changing the water. Rinse thoroughly with clean water. Allow to dry.

#### Additional Surface Preparation

Galvanising Bright galvanised surfaces should be pre-treated with T Wash. Overall blackening of the surface will confirm satisfactory surface preparation. When dry prime with one coat of Rust Inhibiting Primer or Metal Primer. Undercoat with one coat of Albany Super Primer Undercoat.

# Technical Data Sheet



Non-ferrous Metals	Prime bare metal with one coat of Rust Inhibiting Primer or Metal Primer. Undercoat with one coat of Albany Super Primer Undercoat.
Ferrous Metals	Remove all millscale and rust back to clean bright metal. Remove all residues. Prime within the working day with one coat of Rust Inhibiting Primer or two coats of Metal Primer. Undercoat with one coat of Albany Super Primer Undercoat.
Previously Decorated Surfaces Timber	Treat any knots with two coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with Ready Mixed Filler. Rub down with a suitable grade of abrasive paper prior to applying Albany Super Primer Undercoat. Remove all dust. All surfaces must be suitable dry, and free from anything that will interfere with the adhesion of the materials to be applied. Spot prime bare areas with one coat of Albany Super Primer Undercoat.
Metals	Remove all corrosion or rust back to clean bright metal. Remove all residues. Spot prime bare metal within the working day with one coat of Rust Inhibiting Primer or Metal Primer.
Timber and metals	Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Any glossy or eggshell surfaces must be wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. Bring forward spot primed areas and undercoat overall with Albany Super Primer Undercoat.
<b>COATING SYSTEM</b>	For best results apply two coats of Albany Super Gloss. Certain colours may require additional coats to give complete obliteration. Newly painted doors and windows should not be closed until the paint is fully dry.
<b>APPLICATION</b>	Stir well before use. Apply by brush or roller to assist application on porous substrates the surface may be dampened slightly. Maintain a wet edge. On timber lay off in the direction of the grain. Avoid excessive de-nibbing in-between coats. For spray application dilution may be required (dilution may be required. Always intermix packs for colour consistency. Please check for colour accuracy prior to application. Brewers is not liable for decorating costs caused as a result of an incorrect colour being applied.
<b>CLEANING</b>	Return surplus material to container. Wash with clean water immediately after use.
<b>MAINTENANCE INFORMATION FOR CDM FILE</b>	Between maintenance redecoration surfaces may be washed with a warm water and liquid detergent solution to remove surface dirt.
<b>HEALTH AND SAFETY</b>	Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Albany products are freely available from the place of purchase or the address below. Store in secure dry conditions between 5°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.
<b>GENERAL INFORMATION</b>	Apply all products in accordance with BS 6150: 2019 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative

# Technical Data Sheet



---

wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Brewers are unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product please ensure you have the latest information. For help or more information contact:

Brewers  
Tel: 01323 411080  
E-mail: [enquiries@brewers.co.uk](mailto:enquiries@brewers.co.uk)  
Website [www.brewers.co.uk](http://www.brewers.co.uk)

This information is correct at date of issue September 2023.