



BEDEC PRODUCTS LTD.

Surface Coating Specialists

UNITS 1 & 2, POPLARS FARM, AYTHORPE RODING, DUNMOW, ESSEX CM6 1RY
TEL: 01279 876 657 FAX: 01279 876 008 email: info@bedec.co.uk Web site www.bedec.co.uk

Bedec Dark Grey primer undercoat (PAD004)

A high performance cost effective Acrylic primer undercoat specially formulated on an Acrylic binder. Designed for interior and exterior use, providing adhesion promotion on to most substrates and as well as also providing a suitable base before applying acrylic water based or alkyd based enamels.

Suitable substrates.

Bare wood, plaster and porous substrates.

Check for staining. Use Bedec Stain Block where staining may occur

1st coat primer undercoat thinned 25-30% with water.

2nd coat primer undercoat

3rd and 4th coats Gloss or Satin Finish

Ferrous metals.

Check for rust then clean

1st coat oil based anti-corrosive primer

2nd coat primer undercoat

3rd and 4th Gloss or Satin Finish

Non ferrous metals. Galvanising, lead, copper, aluminium etc

Wash with methylated spirit

1st coat primer undercoat.

2nd and 3rd coats Gloss or Satin Finish

Redecoration.

Previously painted surfaces (see preparation)

It is always advisable to key the surface with fine wet and dry.

1st coat primer undercoat.

2nd and 3rd coat Gloss or Satin.

Application

Ensure temperature is above 8 degrees centigrade during application and drying. Do not apply when foggy or damp or likely to rain before the paint has dried.

Brush, Roller or Spray

(Airless Spray -Tip size 13- 17 thou -Pressure 2000-2500 psi)

If conventional air spray or HVLP (high volume low pressure) air spray is being used. We recommend a 1.8mm needle nozzle set up.

Preparation.

Ensure surfaces to be painted are clean dry and free from dust, dirt, grease and wax. Remove all loose and defective paint. Special precautions should be taken during surface preparation



BEDEC PRODUCTS LTD.

Surface Coating Specialists

UNITS 1 & 2, POPLARS FARM, AYTHORPE RODING, DUNMOW, ESSEX CM6 1RY

TEL: 01279 876 657 FAX: 01279 876 008 email: info@bedec.co.uk Web site www.bedec.co.uk

of pre 1960s paint surfaces as they may contain harmful lead. For further information contact customer care.

Algae and fungal growths should be treated with fungicidal wash and removed. Allow new galvanised at least one month to weather before painting. Areas under constant water contact such as showers (hot and cold) are not recommended for water based products.

Drying times

Touch dry in 30 minutes (lower temperatures will extend drying times)

Recoatable 4 to 6 hours.

Fully hardened after one week.

Clean immediately after use with warm soapy water. Remove as much product as possible prior to cleaning.

Coverage

13-15m² per litre

Storage

Replace lid firmly, and protect from low temperatures.

Health and Safety (See COSHH data sheet)

Keep out of reach of children. In case of contact with eyes, rinse immediately with plenty of water. After contact with skin, wash immediately with plenty of water. Ensure good ventilation during application and drying.

Environmental Considerations

Do not empty in to drains or watercourses. Some local authorities have special facilities for disposal or dispensing of waste coatings. To avoid the risk of spillage always store and transport in a secure and upright position. COSHH data sheets are available on request.

EU Limit for this product (A/g): 50g/litre(2007) / 30g/litre(2010) This product contains max 30g/litre

ALTHOUGH EVERY EFFORT SO FAR AS REASONABLY PRACTICABLE HAS BEEN MADE TO ENSURE AT THE DATE OF ISSUE THE ACCURACY OF THE INFORMATION PROVIDED HEREIN, BEDEC PRODUCTS LTD. GIVES NO WARRANTY THAT THE INFORMATION IS ACCURATE AND SHALL IN NO CIRCUMSTANCES BE LIABLE TO ANY PERSON IF IT IS NOT. THE CUSTOMER MUST SATISFY HIMSELF AS TO THE SUITABILITY AND FITNESS FOR HIS PURPOSES OF ANY ARTICLES SUPPLIED BY BEDEC PRODUCTS LTD.