

**RUST-OLEUM®**  
INDUSTRIAL



## COMBIPRIMER® ANTI-RUST PRIMER



# High quality anti-rust primer for CombiColor®

- Recoatable after 2 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# COMBIPRIMER® ANTI-RUST PRIMER

## DESCRIPTION

RUST-OLEUM® CombiPrimer Anti-Corrosion 3369 Red / 3380 Grey are fast drying primers based on an aromatic free short oil alkyd resin. The products contain rust-inhibitive pigments and are lead- and chromate free.

## RECOMMENDED USE

RUST-OLEUM CombiPrimer should be used on new or prepared rusted steel surfaces to provide and enhance protection against corrosion. CombiPrimer Anti-Corrosion is primarily intended for brush application and can also be applied by roller and air spray. CombiPrimer Anti-Corrosion should be used in general industrial exposures, normal humidity and interior applications and should be recoated with CombiColor Original.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,21
Gloss Level:	Matt
Solids content in volume:	44,8%
Heat Resistance:	120°C (dry heat)

## DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour (20°C), 2 hours (10°C), ½ hours (30°C)
Dry to handle:	2 hour (20°C), 4 hours (10°C), 1 hour (30°C)
Dry to recoat:	2 hours (20°C), 4 hours (10°C), 1 hour (30°C)
Fully cured:	7 days (20°C), 14 days (10°C), 5 days (30°C)

## RECOMMENDED WET FILM THICKNESS

80 µm

## RECOMMENDED DRY FILM THICKNESS

35 µm

## THEORETICAL CONSUMPTION

12,8 m<sup>2</sup>/l at 35 µm dry

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2/3 (ISO 8501-1 : 1988). Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APPLICATION & THINNING: BRUSH

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

## APPLICATION & THINNING: ROLLER

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

## CLEANING OF EQUIPMENT / SPILLS

Use RUST-OLEUM Thinner 7301 or white spirit.

## REMARKS

Maximum dry film thickness per coat: 60 µm dry, equals 135 µm wet.

## SAFETY DATA

VOC level:	424 g/l
VOC ready mix:	490 g/l
VOC category:	A/i
VOC limit:	424 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 22/11/2023

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the user's responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)