RUST INHIBITING PRIMER UNDERCOAT

Sandtex Trade Rust Inhibiting Primer Undercoat is formulated for use on exterior metals and is suitable for use on weathered or pre-treated galvanized steelwork. It has excellent rust inhibiting properties and adhesion. Can be overcoated with Sandtex Trade Metalgloss X-tra or Sandtex Trade Eggshell X-tra.

AVAILABILITY

Colour Grey.

Packaging 2.5 litre.

PROPERTIES

Drying time Under normal drying conditions touch dry 4-6 hours and recoatable after 6 hours. Allow for

adequate ventilation during the drying period.

Finish Matt.

Composition Pigment: Titainium dioxide, Talc, Zinc Oxides.

Resin: Tung / Linseed alkyd resin Solvent: Dearomatised White Spirit.

Spreading rate 12m² per litre on smooth surfaces.

Wet film thickness 83 micrometres at 12m² per litre.

Dry film thickness 37 micrometres at 12m² per litre.

Volume solids 44%.

Flash point 41°C (closed cup).

VOC content EU limit value for this product (cat.A/i): 500 g/l (2010)

This product contains max. 499 g/l VOC.

Limitations Do not apply when air or substrate temperatures are likely to fall below 8°C or when the

relative humidity is above 80% during application or the drying period.

PREPARATION
New metal surfaces

Surfaces must be clean and free from anything that will interfere with the materials to be applied. Wash with hot water and liquid detergent solution to remove oil, grease or any other contaminants, frequently changing the water. Rinse thoroughly with clean water. Allow to dry. Galvanised surfaces should be pre-treated with Crown Trade Protective Coatings T Wash. Overall blackening of the surface will confirm satisfactory surface

preparation

Additional surface preparation – all metals

Non-ferrous metals

Lightly abrade to a bright (not polished) surface - excluding galvanised surfaces. Rinse

thoroughly with clean water to remove all resides. Allow to dry.

Ferrous metals

Remove all millscale and rust back to clean metal. Remove all residues.

Priming

Prime all areas to be decorated within the working day, with one coat of Sandtex Trade Rust Inhibiting Primer Undercoat. The wet film thickness must not be less than 83 micrometres. Allow a minimum drying time of 6 hours in normal drying conditions.

Previously decorated metal surfaces

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose and failing or suspect paint. Feather edges of sound paint. Remove all dust. Remove all rust. Spot prime all bare metalwork with Sandtex Trade Rust Inhibiting Primer Undercoat. Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Wet abrade to provide a key. Rinse with clean water to remove all residues. Allow to dry.

COATING SYSTEM Apply one coat to bare metal. On previously painted surfaces apply one coat overall.

APPLICATION Stir well before use. Apply by brush or roller.

CLEANING Return surplus material to container. Clean with a proprietary cleaner immediately after

use.

HEALTH AND SAFETY Please refer to the Safety, Health and Environmental Information on the container. Take

special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing the surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Sandtex products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by the manufacturer as it has no control over the conditions under which its products are applied.

For help or more information contact our Customer Relations Team on 0330 0240 302. Before using this product please ensure you have the latest information. The information is correct at date of issue April 2015.



Sandtex Trade