

ALBANY ACRYLIC PRIMER UNDERCOAT

Versatile formulation for priming / undercoating timber and dry plaster.

AVAILABILITY

Colour	White
Packaging	1, 3 & 5 litres.

PROPERTIES

Drying time	Under normal drying conditions touch dry in 30 minutes and recoatable after 4 hours. Allow for adequate ventilation during the drying period.
Finish	Matt.
Composition	Pigment: Titanium Dioxide and extenders Binder: Acrylic polymer Solvent: Water
Spreading rate	Up to 14m ² per litre depending on surface texture.
Wet film thickness	71 micrometres at 14m ² per litre
Dry film thickness	25 micrometres at 14m ² per litre
Volume solids	35 % Brilliant White.
Flash point	Not applicable
VOC content	EU limit value for this product (cat.A/d): 130 g/l (2010) This product contains max. 1 g/l VOC.
Limitations	For interior and exterior use. Do not apply when there is a risk of rain, air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

PREPARATION

New surfaces	All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Rub down with a suitable grade of abrasive paper. Remove all dust. Timber with oils/extractives must be swabbed with methylated spirits, frequently changing the face of the cloths. Treat knots with two thin coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with a suitable proprietary filler. Rub down with a suitable grade of abrasive paper. Remove all dust.
Previously Decorated Surfaces	All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied e.g. dirt, grease etc. Remove all loose, failing or suspect paint. Feather edges of sound paint. Remove all dust. Organic growth must be removed and the areas treated with a Albany Fungicidal Wash. Fill any fixing holes, cracks and shallow surface defects with a suitable proprietary filler. Patch prime bare and filled areas with Albany Acrylic Primer Undercoat. If after cleaning any areas are still contaminated with substances likely to cause staining and/or bleeding, patch prime with one coat of Albany Primer Sealer.

COATING SYSTEM	Apply two coats as required
APPLICATION	Stir well before use. Apply by brush, roller or spray. For spray application dilution may be required.
CLEANING	Return surplus material to container. Wash with clean water immediately after use.
HEALTH AND SAFETY	Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Albany products are freely available from the place of purchase or the address below. Store in secure dry conditions between 5°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.
GENERAL INFORMATION	Apply all products in accordance with BS 6150: 2019 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Brewers are unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product please ensure you have the latest information. For help or more information contact:

Brewers
Tel: 01323 411080
E-mail: enquiries@brewers.co.uk
Website www.brewers.co.uk

This information is correct at date of issue September 2023.