

Technical Data Sheet

ALBANY WOODCARE – MASTERDEC

Albany MASTERDEC Premium Opaque Satin Finish is a self priming, flexible finish ideal for exterior use. Perfect for windows, doors and cladding to obliterate the original timber colour. MASTERDEC is a water based finish so ideal for working quickly outdoors. Albany MASTERDEC's microporous properties allows the wood to "breathe", resisting cracking, blistering and peeling.

AVAILABILITY

Colour Range Refer to Albany Woodcare literature.
Packaging 1, 2.5 and 5 litres.

PROPERTIES

Drying time Under normal drying conditions touch dry 1-2 hours and recoatable 2-4 hours.
Do not apply in adverse weather conditions.

Finish Satin

Composition Titanium Dioxide and lightfast colour pigments
Binder: alkyd/acrylic resin
Thinner: Water

Spreading rate 12m² per litre, depending on the nature and porosity of the timber.

Wet film thickness 83 microns.

Dry film thickness 35 microns.

Flash Point Not Applicable

VOC Content EU limit value for this product (Cat A/e): 130g/l (2010).
This product contains max 50g/l VOC.
LOW VOC CONTENT 0.3-7.99%.

PREPARATION

General Timber All surfaces must be clean, dry and free from loose and flaking material. Old paint and varnish should be completely removed. Ensure that all timbers to be treated are sound, dry and free from dirt, dust, grease or any other surface contaminants. Treat any mould or lichen with Albany Fungicidal Wash. Softwood intended for exterior use which has not already been pre-treated should first be given a coat of clear preservative. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Special precautions should be taken during surface preparation of pre 1960s paint surfaces over wood and metal as they may contain harmful lead.

New Timber All surfaces must be clean, dry and free from loose and flaking material. Old paint and varnish should be completely removed. Ensure that all timbers to be treated are sound, dry and free from dirt, dust, grease or any other surface contaminants. Coat any non-treated wood with two coats of Albany MASTERDEC, in the direction of the grain. Allow 2-4 hours before overcoating.

Previously Painted All surfaces must be sound, suitably dry and free from anything that could interfere with the adhesion of the material to be applied.

Remove any defects such as flaking or cracked paint and fill any crack or joints with wood filler.

COATING SYSTEM 1-2 coats.

APPLICATION Stir well before use, Apply by brush, working well into the material, along the timber grain.

ALBANY WOODCARE – MASTERDEC

CLEANING	Wash immediately after use with warm soapy water.
MAINTENANCE INFORMATION FOR CDM FILE	Maintenance requirement can be indicated by lightening of colour, reduction in sheen or a loss of water repellence. When you begin maintenance redecoration, ensure surfaces are washed with a warm water and liquid detergent solution to remove any surface dirt, rinse with clean water and allow to dry before overcoating
HEALTH AND SAFETY	Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Albany products are freely available from the place of purchase or the address below. Store in secure dry conditions between 10°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2019 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. C Brewer & Sons Ltd are unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product, please ensure you have the latest information.

For help or more information contact:

Brewers
Tel **01323 411080**
E-mail **enquiries@brewers.co.uk**
Website **www.brewers.co.uk**

This information is correct at date of issue April 2024